

PRODUCT SPECIFICATION OF FILTRALITE®

Filter media

FILTRALITE® NC 1,5-2,5

Commercial name	FILTRALITE® NC 1,5-2,5 mm
Density	Bulk density: 320 kg/m ³ particle density: 720 kg/m ³
Type of material	Expanded clay
Appearance	Crushed particles, porous surface structure
Manufactured by	maxit Leca Rælingen, Norway

Size and weight	Value	Deviation	Comments
Effective size	1,7 mm	± 0,3 mm	d ₁₀
Particle size range	1,5-2,5 mm	< 1,4 mm max. 5 % +Δ < 0,125 mm > 2,5 mm max. 5 %	
Coefficient of uniformity	< 1,5		d ₆₀ / d ₁₀ ,
Bulk density, dry	320 kg/m ³	± 75 kg/m ³	EN 1097-3
Particle density, dry (PDD)	720 kg/m ³	± 150 kg/m ³	Exclay Norm
Particle density, wet			
After 1 day in water	1038 kg/m ³	± 150 kg/m ³	
After 300 days in water	1115 kg/m ³	± 150 kg/m ³	

Other properties	Value	Comments
Particle porosity	73 %	Porosity internal particle: $(1 - PDD/2700 \text{ kg/m}^3) * 100$
Voids	67 %	EN 1097-3
Acid solubility	< 5 %	EN 12902

Chemical composition, average values:

SiO ₂	Al ₂ O ₃	FeO ₃	K ₂ O	MgO	CaO	Na ₂ O	C _{tot}
62%	18%	7%	4%	3%	3%	2%	0,02%

As the particle density in dry conditions is lower than the density of water, parts of the material will float until it is saturated with water.

maxit as P.O. Box 216 Alnabru 0614 Oslo, Norway	<u>Further information:</u> www.filtralite.com E-mail: info@filtralite.com	<u>Telephone:</u> +47 22 88 77 00 <u>Telefax:</u> +47 22 64 54 54
--	---	--


