

PRODUCT SPECIFICATION OF FILTRALITE®

Filter media

FILTRALITE® MC 2,5-4

Commercial name	FILTRALITE® MC 2,5-4 mm
Density	Bulk density: 625 kg/m ³ particle density: 1200 kg/m ³
Type of material	Expanded clay
Appearance	Crushed particles, porous surface structure
Manufactured by	Weber Leca Rælingen, Norway

Size and weight	Value	Deviation	Comments
Effective size	2,6 mm	± 0,15 mm	d ₁₀
Particle size range	2,5-4 mm	< 2,0 mm max. 3 % +Δ < 0,125 mm > 4,0 mm max. 5 %	
Coefficient of uniformity	< 1,5		d ₆₀ / d ₁₀
Bulk density, dry	625 kg/m ³	± 75 kg/m ³	EN 1097-3
Particle density, dry (PDD)	1200 kg/m ³	± 150 kg/m ³	Exclay Norm

Other properties	Value	Comments
Floating particles	< 2%	Maximum volume floating particles after 2 days in water.
Particle porosity	56%	Porosity internal particle: (1-PDD/2700 kg/m ³)*100
Voids	48 %	EN 1097-3
Acid solubility	< 5 %	EN 12 902
Water adsorption 24 hours	20 %	Approximately value. Exclay Norm
Water adsorption 1 month	40 %	Approximately value. Exclay Norm

Chemical composition, average values:

SiO ₂	Al ₂ O ₃	FeO ₃	K ₂ O	MgO	CaO	Na ₂ O	C _{tot}
62%	18%	7%	4%	3%	3%	2%	0,02%

Weber

Saint-Gobain Byggevarer AS
P.O. Box 216 Alnabru
0614 Oslo, Norway

Further information:
www.filtralite.com
E-mail: info@weber-norge.no

Telephone:
+47 22 88 77 00
Telefax:
+47 22 64 54 54


